Hangzhou Jiekai Chemicals Co., Ltd.

NO.227, SHIXIN BEILU RD, HANGZHOU, CHINA. Tel: 86-571-83710202 Web: www.jkpigment.com

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Page:1/3			
1. Identification of substance and of the company			
Trade Name: PIGMENT YELLOW 1			
Hangzhou Jiekai Chemicals Co., Ltd.			
NO.227, SHIXIN BEILU RD, XIAOSHAN DISTRICT, HANGZHOU, CHINA.			
Tel: 86-571-83710202 Fax: 86-571-82163005			
2. <u>Composition/Data on components</u>			
Substance: Pigment Yellow 1			
CAS No: 2512-29-0 EEC Symbol: None R-Phrases: None			
3. <u>Hazards identification</u>			
No hazardous effects known			
The product is not a substance subject to mandatory marking in accordance with the EEC			
Directive 67/584/EEC Or amendments			
4. <u>First Aid measures</u>			
After inhalation: Supply fresh air.			
After eye contact: Flush with plenty of pressure water for 15 minutes, occasionally raising			
eye lids.			
After skin contact: Wash skin with mild soap and water.			
5. <u>Fire fighting measures</u>			
Suitable extinguishing media: no restriction			
Special hazards caused by the material, its combustion products or resultant gases: none			
Special personal protection equipment: none			
6. <u>Accidental release</u>			
Environmental protection conduct: Do not sweep or wash into public stretches of water,			
sewers or sites of unknown discharge paths.			
After spillage/leakage/gas/ leakage: Clean up immediately with wetting or absorbent			
material avoiding dusting.			
7. <u>Handling and storage</u>			
Handling:			
Usual precautions for nuisance dust should be observed.			
Protection against fire and explosion:			
The product is non-flammable			
Storage:			
Store in roofed places at room temperature Keep containers tightly sealed.			
Flammability Class: nor applicable.			

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

	-		Page:2/.
Trade name: PIGMENT Y	TELLOW 1		
8. <u>Exposure controls/</u>	personal protection	1	
Additional notes for d	esign of plants equipr	nent:	
No farther details, see s	sec7		
Components with wor	kplace-related limits	to be monitored:	
Designation	%	Type of data	Unit
Nuisance dust	100	MAK	6 mg/m3
		TLV/TWA(USA)	10 mg/m3
Personal protection e	quipment:		
Respiratory protectio	n:		
An appropriate dust fix	er has to be used if a b	reathable dust liberated.	
9. <u>Physical and chem</u>	ical properties		
Appearance: yellow po	wder	Odor: mild	
Melting point: 256°C		Relative density:1.6	
Decomposition: None		Flammability: see 6 handling	
Molecular formula: C17H18N4O4		Molecular Weight: 340.33	
Tinting strength: 95-105% of the standardVolatile matter at 105 °C: 2.5% m		2: 2.5% max	
Soluble matter in water: 1.5% max			
Fastness to light:6		Fastness to heat(°C):160	
Bleeding resistance water: 4		Bleeding resistance linseed oil: 4	
Bleeding resistance acid: 5		Bleeding resistance alkalis:5	
Bleeding resistance alcohol: 5		Bleeding resistance xylone:4	
Bleeding resistance eth	yl acetate: 4		
10. <u>Stability and reac</u>	<u>tivity</u>		
Hazardous decomposi	tion products		
No decomposition at]	proper storage and appl	ication conditions	
11. <u>Toxicological Info</u>	<u>rmation</u>		
Because of experience	e with product mention	ed, there are no recognizable	e hazards for huma
beings, if it is correctl	y used and applied.	_	
12. <u>Ecological inform</u>	atio		
Avoid filtration into w	vaster draining or soil.		
13. <u>Disposal consider</u>			
-	themselves with local r	-	
		an approved tip or by incine eed to be sorubbed (see section	-

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Page:3/3

Trade name: PIGMENT YELLOW 1

14. <u>Transport information</u>

No declaration for transport required

15. <u>Regulatory information</u>

Classified according to the Directives 67/548/EEC, and their varions amendments, and labeled as below:

Warning symbols: None

Warning words: None

Risk Phrases: None

Safety Phrases: None

16. Other information

Listed in EINECS and TSCA inventories.0

Intended uses: Paints.

References: -(1)Occupational Exposure Limits, EH/40(HSE)

-(2)Deutsche Forschungs gerneinschaft MAK-& BAT-Values.

-(3)A.C.D.Cowley, Polymers Paint Journal, August 7/21, 1985.