Hangzhou Jiekai Chemicals Co., Ltd.

NO.227, SHIXIN BEILU RD, HANGZHOU, CHINA. Tel: 86-571-83710202 Web: www.jkpigment.com

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Page:1/3				
1. Identification of substance and of the company				
Trade Name: PIGMENT YELLOW 151				
Hangzhou Jiekai Chemicals Co., Ltd.				
NO.227, SHIXIN BEILU RD, XIAOSHAN DISTRICT, HANGZHOU, CHINA.				
Tel: 86-571-83710202 Fax: 86-571-82163005				
2. <u>Composition/Data on components</u>				
Substance: Pigment Yellow 151				
CAS No: 31837-42-0 EEC Symbol: None R-Phrases: None				
3. Hazards identification				
No hazardous effects known				
The product is not a substance subject to mandatory marking in accordance with the EEC				
Directive 67/584/EEC Or amendments				
4. <u>First Aid measures</u>				
After inhalation: Supply fresh air.				
After eye contact: Flush with plenty of pressure water for 15 minutes, occasionally raising				
eye lids.				
After skin contact: Wash skin with mild soap and water.				
5. <u>Fire fighting measures</u>				
Suitable extinguishing media: no restriction				
Special hazards caused by the material, its combustion products or resultant gases: none				
Special personal protection equipment: none				
6. Accidental release				
Environmental protection conduct: Do not sweep or wash into public stretches of water,				
sewers or sites of unknown discharge paths.				
After spillage/leakage/gas/ leakage: Clean up immediately with wetting or absorben				
material avoiding dusting.				
7. <u>Handling and storage</u>				
Handling:				
Usual precautions for nuisance dust should be observed.				
Protection against fire and explosion:				
The product is non-flammable				
Storage:				
Store in roofed places at room temperature Keep containers tightly sealed.				
Flammability Class: nor applicable.				

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

			Page:2/.
Frade name: PIGMENT YE			
8. <u>Exposure controls/pe</u>			
Additional notes for des		ment:	
No farther details, see sec			
Components with work	•		TT T
Designation	<u>%</u>	Type of data	<u>Unit</u>
Nuisance dust	100	MAK	6 mg/m3
D	•	TLV/TWA(USA)	10 mg/m3
Personal protection equ	ipment:		
Respiratory protection:	1 4 1 1.0 1	4 11 1 411 4 1	
An appropriate dust fixer		breathable dust liberated.	
). <u>Physical and chemica</u>	al properties		
Appearance: yellow powe	lor	Odor: mild	
Decomposition: None		Flammability: see 6 handling	
Molecular formula: C18H15N505		Molecular Weight: 381.34	
Tinting strength: 95-105%		Volatile matter at 105° C: 2.5% max	
Soluble matter in water: 1		Oil absorption: 45%	
Fastness to light:8		Fastness to heat ($^{\circ}$ C):210	
Bleeding resistance water: 5		Bleeding resistance linseed oil: 5	
Bleeding resistance acid: 5		Bleeding resistance alkalis:5	
Bleeding resistance alcoh		Bleeding resistance xylone:5	
Bleeding resistance ethyl		<i>, , , , , , , , , ,</i>	
10. <u>Stability</u> and reactiv			
Hazardous decomposition			
No decomposition at pro		lication conditions	
11. <u>Toxicological Inforr</u>	nation		
Because of experience w	with product mention	ned, there are no recognizable	hazards for huma
beings, if it is correctly u	-	ied, mere are no recognizable	c nazards for numa
12. <u>Ecological informat</u>			
	10		
Avoid filtration into was	ter draining or soil		
Trong Inflation into was	the artilling of 5011.		
13. <u>Disposal considerat</u>			
Uses should acquaint the			
		an approved tip or by incine	-
waste material processor	r; stack gases may n	eed to be sorubbed (see section	on 5 above)

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Page:3/3

Trade name: PIGMENT YELLOW 151

14. <u>Transport information</u>

No declaration for transport required

15. <u>Regulatory information</u>

Classified according to the Directives 67/548/EEC, and their varions amendments, and labeled as below:

Warning symbols: None

Warning words: None

Risk Phrases: None

Safety Phrases: None

16. Other information

Listed in EINECS and TSCA inventories.0

Intended uses: Paints.

References: -(1)Occupational Exposure Limits, EH/40(HSE)

-(2)Deutsche Forschungs gerneinschaft MAK-& BAT-Values.

-(3)A.C.D.Cowley, Polymers Paint Journal, August 7/21, 1985.