Hangzhou Jiekai Chemicals Co., Ltd.

NO.227, SHIXIN BEILU RD, HANGZHOU, CHINA. Tel: 86-571-83710202 Web: www.jkpigment.com

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Page:1/3
1. Identification of substance and of the company
_
Trade Name: PIGMENT YELLOW 154
Hangzhou Jiekai Chemicals Co., Ltd.
NO.227, SHIXIN BEILU RD, XIAOSHAN DISTRICT, HANGZHOU, CHINA.
Tel: 86-571-83710202 Fax: 86-571-82163005
2. <u>Composition/Data on components</u>
Substance: Pigment Yellow 154
CAS No:68134-22-5 EEC Symbol: None R-Phrases: None
3. <u>Hazards identification</u>
No hazardous effects known
The product is not a substance subject to mandatory marking in accordance with the EEC
Directive 67/584/EEC Or amendments
4. <u>First Aid measures</u>
After inhalation: Supply fresh air.
After eye contact: Flush with plenty of pressure water for 15 minutes, occasionally raising
eye lids.
After skin contact: Wash skin with mild soap and water.
5. <u>Fire fighting measures</u>
Suitable extinguishing media: no restriction
Special hazards caused by the material, its combustion products or resultant gases: none
Special personal protection equipment: none
6. <u>Accidental release</u>
Environmental protection conduct: Do not sweep or wash into public stretches of water,
sewers or sites of unknown discharge paths.
After spillage/leakage/gas/ leakage: Clean up immediately with wetting or absorbent
material avoiding dusting.
7. <u>Handling and storage</u>
Handling:
Usual precautions for nuisance dust should be observed.
Protection against fire and explosion:
The product is non-flammable
Storage:
Store in roofed places at room temperature Keep containers tightly sealed.
Flammability Class: nor applicable.

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

		Page:2/.
Trade name: PIGMENT YELLOW 154		
8. <u>Exposure controls/personal protection</u>		
Additional notes for design of plants equip	ment:	
No farther details, see sec7		
Components with workplace-related limits		
Designation %	Type of data	Unit
Nuisance dust 100	MAK	6 mg/m3
	TLV/TWA(USA)	10 mg/m3
Personal protection equipment:		
Respiratory protection:		
An appropriate dust fixer has to be used if a b	reathable dust liberated.	
9. <u>Physical and chemical properties</u>		
Appearance: yellow powder	Odor: mild	
Melting point:	Relative density:1.5	
Decomposition: None	Flammability: see7 handling	
Molecular formula: C18H14F3N503	Molecular Weight: 405.33	
Tinting strength: 95-105% of the standard	Volatile matter at 105°C: 2.5% max	
Soluble matter in water: 1.5% max	Oil absorption: 40-60%	
Fastness to light:7-8	Fastness to heat(°C):260	
Bleeding resistance water: 5	Bleeding resistance linseed oil: 5	
Bleeding resistance acid: 5	Bleeding resistance alkalis:3-4	
Bleeding resistance alcohol: 5	Bleeding resistance xylone:5	
Bleeding resistance ethyl acetate: 4-5		
10. <u>Stability and reactivity</u>		
Hazardous decomposition products		
No decomposition at proper storage and app	lication conditions	
11. <u>Toxicological Information</u>		
Because of experience with product mention	ed, there are no recognizable	e hazards for huma
beings, if it is correctly used and applied.	<i>c</i> , <i>c c c c c c c c c c</i>	
12. <u>Ecological informatio</u>		
Avoid filtration into waster draining or soil.		
13. <u>Disposal considerations</u>		
Uses should acquaint themselves with local i		
Disposal is usually carried out by burying at		-
waste material processor; stack gases may ne	eed to be sorubbed (see section	on 5 above)

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Page:3/3

Trade name: PIGMENT YELLOW 154

14. <u>Transport information</u>

No declaration for transport required

15. <u>Regulatory information</u>

Classified according to the Directives 67/548/EEC, and their varions amendments, and labeled as below:

Warning symbols: None

Warning words: None

Risk Phrases: None

Safety Phrases: None

16. Other information

Listed in EINECS and TSCA inventories.0

Intended uses: Paints.

References: -(1)Occupational Exposure Limits, EH/40(HSE)

-(2)Deutsche Forschungs gerneinschaft MAK-& BAT-Values.

-(3)A.C.D.Cowley, Polymers Paint Journal, August 7/21, 1985.