# Hangzhou Jiekai Chemicals Co., Ltd.

NO.227, SHIXIN BEILU RD, HANGZHOU, CHINA. Tel: 86-571-83710202 Web: www.jkpigment.com

# **Material Safety Data Sheet**

According to 91/155/EEC and ISO 11014-1

**Page:1/3** 

# 1. Identification of substance and of the company

Trade Name: PIGMENT RED 48:3 Hangzhou Jiekai Chemicals Co., Ltd.

NO.227, SHIXIN BEILU RD, XIAOSHAN DISTRICT, HANGZHOU, CHINA.

Tel: 86-571-83710202 Fax: 86-571-82163005

# 2. Composition/Data on components

Substance: PIGMENT RED 48:3

CAS No: 15782-05-5 EEC Symbol: None R-Phrases: None

# 3. Hazards identification

No hazardous effects known

The product is not a substance subject to mandatory marking in accordance with the EEC Directive 67/584/EEC Or amendments

# 4. First Aid measures

**After inhalation:** Supply fresh air.

After eye contact: Flush with plenty of pressure water for 15 minutes, occasionally raising

eye lids.

After skin contact: Wash skin with mild soap and water.

# 5. Fire fighting measures

Suitable extinguishing media: no restriction

Special hazards caused by the material, its combustion products or resultant gases: none

Special personal protection equipment: none

## 6. Accidental release

**Environmental protection conduct:** Do not sweep or wash into public stretches of water, sewers or sites of unknown discharge paths.

**After spillage/leakage/gas/ leakage:** Clean up immediately with wetting or absorbent material avoiding dusting.

## 7. Handling and storage

#### **Handling:**

Usual precautions for nuisance dust should be observed.

#### Protection against fire and explosion:

The product is non-flammable

#### Storage:

Store in roofed places at room temperature Keep containers tightly sealed.

Flammability Class: nor applicable.

## **Material Safety Data Sheet**

According to 91/155/EEC and ISO 11014-1

Page:2/3

Trade name:	<b>PIGMENT</b>	RFD	48.3
Trade name.	I ICHVILLINI	NED	+())

## 8. Exposure controls/personal protection

## Additional notes for design of plants equipment:

No farther details, see sec7

#### Components with workplace-related limits to be monitored:

Designation	%	Type of data	Unit
Nuisance dust	100	MAK	6 mg/m3
		TLV/TWA(USA)	10 mg/m3

#### **Personal protection equipment:**

#### **Respiratory protection:**

An appropriate dust fixer has to be used if a breathable dust liberated.

# 9. Physical and chemical properties

Appearance: Red powder Odor: mild

Melting point:

Relative density:1.61-1.90

Decomposition: None

Flammability: see 7handling

Molecular formula:C18H15ClN2O6S

Molecular Weight: 422.84

Tinting strength: 95-105% of the standard Volatile matter at 105°C: 2.5% max

Bleeding resistance water: 5

Bleeding resistance linseed oil: 5

Bleeding resistance alkalis:4

Bleeding resistance alcohol:3

Bleeding resistance xylone:3-4

Bleeding resistance ethyl acetate: 3-4

# 10. Stability and reactivity

Hazardous decomposition products

No decomposition at proper storage and application conditions

## 11. Toxicological Information

Because of experience with product mentioned, there are no recognizable hazards for human beings, if it is correctly used and applied.

## 12. Ecological informatio

Avoid filtration into waster draining or soil.

# 13. Disposal considerations

Uses should acquaint themselves with local regulations.

Disposal is usually carried out by burying at an approved tip or by incineration by a licensed waste material processor; stack gases may need to be sorubbed (see section 5 above)

# **Material Safety Data Sheet**

According to 91/155/EEC and ISO 11014-1

Page:3/3

## Trade name: PIGMENT RED 48:3

# 14. Transport information

No declaration for transport required

# 15. Regulatory information

Classified according to the Directives 67/548/EEC, and their varions amendments, and

labeled as below:

Warning symbols: None Warning words: None Risk Phrases: None Safety Phrases: None

# 16. Other information

Listed in EINECS and TSCA inventories.0

Intended uses: Paints.

References: -(1)Occupational Exposure Limits, EH/40(HSE)

-(2)Deutsche Forschungs gerneinschaft MAK-& BAT-Values. -(3)A.C.D.Cowley, Polymers Paint Journal, August 7/21, 1985.