Hangzhou Jiekai Chemicals Co., Ltd.

NO.227, SHIXIN BEILU RD, HANGZHOU, CHINA. Tel: 86-571-83710202 Web: www.jkpigment.com

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Page:1/3

1. Identification of substance and of the company

Trade Name: PIGMENT RED 63:1 Hangzhou Jiekai Chemicals Co., Ltd.

NO.227, SHIXIN BEILU RD, XIAOSHAN DISTRICT, HANGZHOU, CHINA.

Tel: 86-571-83710202 Fax: 86-571-82163005

2. Composition/Data on components

Substance: PIGMENT RED 63:1

CAS No: 6417-83-0 EEC Symbol: None R-Phrases: None

3. Hazards identification

No hazardous effects known

The product is not a substance subject to mandatory marking in accordance with the EEC Directive 67/584/EEC Or amendments

4. First Aid measures

After inhalation: Supply fresh air.

After eye contact: Flush with plenty of pressure water for 15 minutes, occasionally raising

eye lids.

After skin contact: Wash skin with mild soap and water.

5. Fire fighting measures

Suitable extinguishing media: no restriction

Special hazards caused by the material, its combustion products or resultant gases: none

Special personal protection equipment: none

6. Accidental release

Environmental protection conduct: Do not sweep or wash into public stretches of water, sewers or sites of unknown discharge paths.

After spillage/leakage/gas/ leakage: Clean up immediately with wetting or absorbent material avoiding dusting.

7. Handling and storage

Handling:

Usual precautions for nuisance dust should be observed.

Protection against fire and explosion:

The product is non-flammable

Storage:

Store in roofed places at room temperature Keep containers tightly sealed.

Flammability Class: nor applicable.

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Page:2/3

Trade name:	PIGMENT RED	63:1
-------------	-------------	------

8. Exposure controls/personal protection

Additional notes for design of plants equipment:

No farther details, see sec7

Components with workplace-related limits to be monitored:

Designation	%	Type of data	Unit
Nuisance dust	100	MAK	6 mg/m3
		TLV/TWA(USA)	10 mg/m3

Personal protection equipment:

Respiratory protection:

An appropriate dust fixer has to be used if a breathable dust liberated.

9. Physical and chemical properties

Appearance: Red powder Odor: mild

Melting point : $^{\circ}$ C Relative density: 1.80

Decomposition: None Flammability: see 7handling Molecular formula:C18H14N2O6S Molecular Weight: 422.41

Tinting strength: 95-105% of the standard Volatile matter at 105°C: 2.5% max

Soluble matter in water: 1.5% max

Oil absorption:45-55%

Fastness to light:6

Fastness to heat(°C):160

Bleeding resistance water: 4 Bleeding resistance linseed oil:5
Bleeding resistance acid:4 Bleeding resistance alkalis:4
Bleeding resistance alcohol:4-5 Bleeding resistance xylone:4

Bleeding resistance ethyl acetate: 3

10. Stability and reactivity

Hazardous decomposition products

No decomposition at proper storage and application conditions

11. Toxicological Information

Because of experience with product mentioned, there are no recognizable hazards for human beings, if it is correctly used and applied.

12. Ecological informatio

Avoid filtration into waster draining or soil.

13. Disposal considerations

Uses should acquaint themselves with local regulations.

Disposal is usually carried out by burying at an approved tip or by incineration by a licensed waste material processor; stack gases may need to be sorubbed (see section 5 above)

Material Safety Data Sheet

According to 91/155/EEC and ISO 11014-1

Page:3/3

Trade name: PIGMENT RED 63:1

14. Transport information

No declaration for transport required

15. Regulatory information

Classified according to the Directives 67/548/EEC, and their varions amendments, and

labeled as below:

Warning symbols: None Warning words: None Risk Phrases: None Safety Phrases: None

16. Other information

Listed in EINECS and TSCA inventories.0

Intended uses: Paints.

References: -(1)Occupational Exposure Limits, EH/40(HSE)

-(2)Deutsche Forschungs gerneinschaft MAK-& BAT-Values. -(3)A.C.D.Cowley, Polymers Paint Journal, August 7/21, 1985.